



VFI-3400-2 COMPONENT AROMATIC POLYURETHANE DECK BASECOAT

Overview

- Description**
 VFI-3400 is a 2 component, aromatic polyurethane coating that can be batch mixed at an easy 1:1 by volume ratio for decking and coating projects. VFI-3400 offers good pot life and produces an elastomer with excellent impact and waterproofing properties. This product should be topcoated with VFI-3500 if used externally for a concrete decking basecoat.
- Usage**
 VFI-3400 applications include:
 - Basecoat for concrete decking
 - Poured in potting and molding
 - Sealant, caulk and filler
 - Low temperature flexible molds
- Color**
 Standard color is light gray.

Physical Properties

- Hardness**
 ASTM D-2240
 Shore A 70-75
 Shore D 20-25
- Tensile Properties**
 ASTM D-412
 Strength 1000-1300 psi
 Elongation 400%
 Elastic Modulus 800-1400 psi
- Tear Strength**
 ASTM D-624 (Die C) 130 pli
- Solid Material Density**
 66.30 pcf
- Dimensional Stability**
 Shrinkage .010-.030%
 Depending on cure temperature.

Weather & Environmental Performance

- Service Temperature**
 -30 °F to 180 °F.
- Weatherability**
 VFI-3400 is an Aromatic Polyurethane. It is intended to be topcoated with VFI-3500 or a similar aliphatic, light UV stable material.

Liquid Component Properties

- Ratio**
 - By Volume**
 "A" side 1
 "B" side 1
 - By Weight**
 "A" side 112
 "B" side 100
- Viscosity**
 "A" side 400-800 cps @ 77°F
 "B" side 400-800 cps @ 77°F
- Liquid Density & Specific Gravity**
 "A" side 9.35 lbs/gal (SG 1.12)
 "B" side 8.35 lbs/gal (SG 1.00)
- VOC**
 Contains no volatile organic compounds.

- **Toxicity**
ISO component contains MDI Isocyanate requiring respirator, gloves, eye protection and protective clothing during application.
- **Reactivity**
 - **Pot Life:** 20-25 minutes at 77°F
 - **Gel Time:** 25-30 minutes at 77°F
 - **Recoat Time:** 4-48 hours at 77°F
 - **Cure Time:** Full properties reached in 3-5 days at 77°F.

*The substrate and ambient temperature will affect all reactivity data. Cooler temperatures will be longer and hotter temperatures will be quicker.

- **Storage Stability or Shelf Life**
 - **“A” side:** 6 months in unopened containers @ 60-90°F. The “A” side must remain stored in tightly sealed containers without exposure to moisture. If material freezes, heat in a convection oven to 150°F to melt to a liquid.
 - **“B” side:** 12 months in unopened containers @ 60-90° F. The “B” side is moisture absorbent. Keep unused material sealed to prevent moisture absorption.

Application

- **Equipment**
Hand mix, power mix or injection equipment. For equipment requirements and specific instructions, contact Volatile Free, Inc.
- **Material Preparation**
The product must be over 70° F for proper mixing. The Poly B side must be premixed slowly, at low rpm before using at low rpm (to minimize air entrapment) before mixing 1:1 with ISO A side.
- **Mixing**
VFI-3400 is a 2 component 1:1 by volume material. Measure out equal volumes of ISO A side and Poly B side (after this is separately mixed until uniform for 5-10 minutes) into a mixing container. Mix thoroughly and continuously for 2-5 minutes until a homogenous, gray color is present with no streaks present.
- **Concrete Deck Application**
Refer to VFI-3500 for Application instructions.
- **Limitations**
To verify this product is appropriate for your specific application, consult with Volatile Free, Inc.'s technical department
- **Clean-up Solvent**
Xylene, MEK. For reduced fire hazard use glycol ethers or environmentally acceptable chlorinated solvents.
- **Precautions**
See Safety Data Sheet for complete safety data.
- **Thinning**
Do not thin this material with any solvents.
- **Packaging**
 - 5 gallon pails
 - 15 gallon ponies
 - 55 gallon drums
 - 270 gallon totes

For more information, contact us today at **800-307-9218**

Corporate Office: P.O. Box 344 • Brookfield, WI 53008 • (800) 307-9218 • (262) 787-0400 • Fax (262) 787-0500 • www.volatilefree.com

This information and technical advice provided herein are believed to be reliable and accurate to the best knowledge of Volatile Free, Inc. As based on tests and should serve only as a recommendation. As the manufacturer, Volatile Free, Inc makes no representations or warranties of any kind, expressed, implied or statutory, including but not limited to all implied warranties of merchantability or fitness for use or a particular purpose, or any other matter with respect to this product. Volatile Free, Inc makes no representations or warranties as to the results of the use of the product and assumes no obligation or liability in connection therewith. Volatile Free, Inc is not liable for any special, exemplary, punitive, incidental or consequential damages of any sort or kind from use of this product. The information provided herein is subject to change at any time without notice. Information changes may include, but are not limited to, commercial and technical changes, changes in pricing, physical characteristics and packaging.